



## TEST REPORT

No. : AX170 ~~AX170-0001-0001~~

Date : Oct 23, 2019

Page: 1 of 5

CUSTOMER NAME: ARMOUR-X PPF

The following sample's information(s) was/ were submitted and identified on behalf of the client as:

**Sample Name** : ARMOUR-X Paint Protection Film  
**SGS Ref No.** : AX170 ~~AX170-0001-0001~~  
**Date of Receipt** : Sep 25, 2020  
**Testing Start Date** : Sep 26, 2020  
**Testing End Date** : Oct 18, 2030  
**Test Result(s)** : For further details, please refer to the following page(s)

Signed for and on behalf of  
SGS-CSTC Standards Technical  
Services(Tianjin) Co., Ltd

-----  
Lisa Jin  
Lab Supervisor

## TEST REPORT

No. : AX17 ~~XXXX-XXXX-XXXX~~

Date : Oct 23, 2019

Page: 2 of 5

### Report Declaration:

The test samples were provided and confirmed by the customer in this report, the results contained in this test report do not relate to other samples of the same product. The manufacturer should ensure that all products manufactured are in conformity with the product sample in this report.

In the territory of the People's Republic of China, the test method is not in CMA accredited scope, the test report shall only be used for client scientific research, teaching, internal quality control, product research and development, etc...and just for client internal reference.

### Manufacture Declaration or Comment:

None

### Summary of Result(s):

No.	Test Item	Test Method	Conclusion
1.	Tensile Test	ASTM D638-14	N/A

### Note:

Pass: Meet the requirements

Fail: Does not meet the requirements

N/A: Not apply to the judgment


## TEST REPORT

No. : AX17 ~~XXXX-XXXX-XXXX~~

Date : Oct 23, 2019

Page: 3 of 5

Original Sample Photo:



Sample A

## TEST REPORT

No. : AX17 ~~XXXX-XXXX-XXXX~~

Date : Oct 23, 2019

Page: 4 of 5

### 1. Test Item: Tensile Test

Test Method: ASTM D638-14

Test Condition:

Specimen: Type I

Specimen thickness: 0.176mm

Testing speed: 50mm/min

Gauge length: 50mm

Distance between grips: 115 mm

Lab Environmental Condition:  $23 \pm 2$  °C,  $50 \pm 5$  % RH

Test Result:

Test Item	Test Result
Tensile Strength	14.7MPa
Elongation at Break	320%

Note:

1. The release paper of test specimens was ripped off before test.
2. Test specimens were cut from the sample.


## TEST REPORT

No. : AX17 ~~XXXX-XXXX-XXXX~~

Date : Oct 23, 2019

Page: 5 of 5

Test Photo:



Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Universal Testing Machine	CMT6103	GZMR-PL-E022	2019-10-12	2030-10-11

\*\*\*\*\* End of report\*\*\*\*\*