



TEST REPORT

No. : AX17 ~~AX17 302 302~~

Date : Oct 23, 2019

Page: 1 of 5

CUSTOMER NAME: ARMOUR-X PPF

The following sample's information(s) was/ were submitted and identified on behalf of the client as:

Sample Name : ARMOUR-X Paint Protection Film
SGS Ref No. : AX170 ~~AX17 302 302~~
Date of Receipt : Sep 25, 2020
Testing Start Date : Sep 26, 2020
Testing End Date : Oct 18, 2030
Test Result(s) : For further details, please refer to the following page(s)

Signed for and on behalf of
SGS-CSTC Standards Technical
Services(Tianjin) Co., Ltd

Lisa Jin
Lab Supervisor

TEST REPORT

No. : AX17 ~~XXXX-XXXX-XXXX~~

Date : Oct 23, 2019

Page: 2 of 5

Report Declaration:

The test samples were provided and confirmed by the customer in this report, the results contained in this test report do not relate to other samples of the same product. The manufacturer should ensure that all products manufactured are in conformity with the product sample in this report.

In the territory of the People's Republic of China, the test method is not in CMA accredited scope, the test report shall only be used for client scientific research, teaching, internal quality control, product research and development, etc...and just for client internal reference.

Manufacture Declaration or Comment:

None

Summary of Result(s):

No.	Test Item	Test Method	Conclusion
1.	90° Peel Strength	ASTM D6252/D6252M-98(2011) and client's requirement	See result

Note:

Pass: Meet the requirements

Fail: Does not meet the requirements

N/A: Not apply to the judgment


TEST REPORT

No. : AX17 ~~XXXX-XXXX-XXXX~~

Date : Oct 23, 2019

Page: 3 of 5

Original Sample Photo:



TEST REPORT

No. : AX17 ~~XXXX-XXXX-XXXX~~

Date : Oct 23, 2019

Page: 4 of 5

1. Test Item: 90° Peel Strength

Test Method: ASTM D6252/D6252M-98(2011) and client's requirement

Test Condition:

Specimen width: 25.5mm

Testing speed: 300mm/min

Lab Environmental Condition: 23 ± 2 °C, 50 ± 5 % RH

Test Result:

Test Item	Test Result	Client's requirement	Conclusion
90° Peel Adhesion Strength	56.2 N/100mm	\	\
Appearance	No residual adhesive tape on the paint, no obvious change in paint	No residual adhesive tape on the paint, no obvious change in paint	Pass

Note:

1. The specimens preparation was completed by client.
2. Test specimens were cut from the sample.


TEST REPORT

No. : AX17 ~~AX17-00000000~~

Date : Oct 23, 2019

Page: 5 of 5

Test Photo:



Equipment Information:

Equipment	Model	Equipment No.	Calibration date	Next Calibration date
Universal Testing Machine	Zwick Z010	POL-022	2019-11-7	2030-11-6

***** End of report*****